

Zeitschrift: Archives des sciences [1948-1980]
Herausgeber: Société de Physique et d'Histoire Naturelle de Genève
Band: 12 (1959)
Heft: 8: Colloque Ampère : Maxwell-Ampère conference

Artikel: Paramagnetic resonance of hydrogen fused silica
Autor: Wieringen, J.S. van / Kats, A.
DOI: <https://doi.org/10.5169/seals-739122>

Nutzungsbedingungen

Die ETH-Bibliothek ist die Anbieterin der digitalisierten Zeitschriften auf E-Periodica. Sie besitzt keine Urheberrechte an den Zeitschriften und ist nicht verantwortlich für deren Inhalte. Die Rechte liegen in der Regel bei den Herausgebern beziehungsweise den externen Rechteinhabern. Das Veröffentlichen von Bildern in Print- und Online-Publikationen sowie auf Social Media-Kanälen oder Webseiten ist nur mit vorheriger Genehmigung der Rechteinhaber erlaubt. [Mehr erfahren](#)

Conditions d'utilisation

L'ETH Library est le fournisseur des revues numérisées. Elle ne détient aucun droit d'auteur sur les revues et n'est pas responsable de leur contenu. En règle générale, les droits sont détenus par les éditeurs ou les détenteurs de droits externes. La reproduction d'images dans des publications imprimées ou en ligne ainsi que sur des canaux de médias sociaux ou des sites web n'est autorisée qu'avec l'accord préalable des détenteurs des droits. [En savoir plus](#)

Terms of use

The ETH Library is the provider of the digitised journals. It does not own any copyrights to the journals and is not responsible for their content. The rights usually lie with the publishers or the external rights holders. Publishing images in print and online publications, as well as on social media channels or websites, is only permitted with the prior consent of the rights holders. [Find out more](#)

Download PDF: 10.07.2025

ETH-Bibliothek Zürich, E-Periodica, <https://www.e-periodica.ch>

Paramagnetic Resonance of Hydrogen Fused Silica

by J. S. VAN WIERINGEN and A. KATS

Philips Research Laboratories, N. V. Philips' Gloeilampenfabrieken,
Eindhoven, Netherlands

Résumé.

La silice fondue purifiée ne montre ni absorption optique ni résonance paramagnétique après irradiation aux rayons X à la température ambiante. Par contre, l'irradiation à la température de l'azote liquide produit deux bandes d'absorption dans l'ultraviolet et un spectre de résonance paramagnétique dont l'intensité croît avec le pourcentage en eau. Les mesures de résonance paramagnétique suggèrent que les centres colorés produisant ces phénomènes sont des atomes d'hydrogène. Ils disparaissent en quelques minutes à une température de 10-20° C au-dessus de celle de l'azote liquide.

Purified fused silica was irradiated with 150 kV X-rays. Irradiation at room temperature resulted neither in coloration, nor in paramagnetic resonance. After irradiation doses of a few million röntgen at liquid nitrogen temperature, however, both coloration in the u.v. part of the spectrum and paramagnetic resonance were found. The latter was measured at 3 cm wave length. The spectrum consisted of two lines of width 1 gauss. Their intensity increases with increasing water content of the samples. The lines are attributed to proton hyperfine splitting. This interpretation was checked by replacing part of the protons by deuterium. From the position of the lines the following parameters were determined: g — factor = 2.003 ± 0.001 and hyperfine parameter $A = 1.428$ MHz. These values, together with the isotropy of the lines, are explained by the assumption that one has to do with hydrogen atoms, trapped in the fused silica network. Similar centres have been found by Livingston a.o. [1] in irradiated HClO_4 , H_2SO_4 and H_3PO_4 . Just as in these acids, the centres in fused silica disappear in less than a few hours at temperatures, higher than about 90° K. It is thought that this occurs because the hydrogen atoms start moving and recombination takes place. The process by which

the centres disappear is probably a bimolecular one and its activation energy is 0.2-0.3 eV.

Ordinary, non-purified fused silica is coloured by X-rays even at room temperature, but the amount of coloration depends on its water content; more water means less coloration [2]. The formation and mobility properties of the hydrogen atoms described here give perhaps an explanation for this. It is supposed that the hydrogen atoms act as carriers for the transport of electrons that are thus able to combine with other centres.

1. LIVINGSTON, R., H. ZELDES and E. H. TAYLOR, *Disc. Faraday Soc.*, *19*, 166-173, (1955).
 2. VAN WIERINGEN, J. S. and A. KATS, *Philips Res. Rep.*, *12*, 432-454 (1957).
-