

Zeitschrift: Archives des sciences [1948-1980]
Herausgeber: Société de Physique et d'Histoire Naturelle de Genève
Band: 13 (1960)
Heft: 9: Colloque Ampère

Artikel: Spin-lattice relaxation in some rare earth ethylsulphates
Autor: Cooke, A.H. / Finn, C.B.P. / Orbach, R.
DOI: <https://doi.org/10.5169/seals-738554>

Nutzungsbedingungen

Die ETH-Bibliothek ist die Anbieterin der digitalisierten Zeitschriften auf E-Periodica. Sie besitzt keine Urheberrechte an den Zeitschriften und ist nicht verantwortlich für deren Inhalte. Die Rechte liegen in der Regel bei den Herausgebern beziehungsweise den externen Rechteinhabern. Das Veröffentlichen von Bildern in Print- und Online-Publikationen sowie auf Social Media-Kanälen oder Webseiten ist nur mit vorheriger Genehmigung der Rechteinhaber erlaubt. [Mehr erfahren](#)

Conditions d'utilisation

L'ETH Library est le fournisseur des revues numérisées. Elle ne détient aucun droit d'auteur sur les revues et n'est pas responsable de leur contenu. En règle générale, les droits sont détenus par les éditeurs ou les détenteurs de droits externes. La reproduction d'images dans des publications imprimées ou en ligne ainsi que sur des canaux de médias sociaux ou des sites web n'est autorisée qu'avec l'accord préalable des détenteurs des droits. [En savoir plus](#)

Terms of use

The ETH Library is the provider of the digitised journals. It does not own any copyrights to the journals and is not responsible for their content. The rights usually lie with the publishers or the external rights holders. Publishing images in print and online publications, as well as on social media channels or websites, is only permitted with the prior consent of the rights holders. [Find out more](#)

Download PDF: 14.07.2025

ETH-Bibliothek Zürich, E-Periodica, <https://www.e-periodica.ch>

Spin-Lattice Relaxation in some Rare Earth Ethylsulphates¹

by A. H. COOKE, C. B. P. FINN and R. ORBACH²

Clarendon Laboratory, Oxford, England

The work of Finn, Orbach and Wolf [1] on spin-lattice relaxation in cerium magnesium nitrate at temperatures in the liquid helium range supports the hypothesis that in this substance the dominant relaxation mechanism is by direct phonon transitions between the states of the ground doublet and a low-lying excited state of the magnetic ions. This 'statistical' process leads to a temperature dependence of the relaxation time T_1 proportional to $\exp(\Delta/kT)$, where Δ is the energy of the excited state.

We have carried out similar investigations on the ethyl-sulphates of neodymium, dysprosium, erbium and ytterbium, in order to discover whether the same mechanism is important in these substances. We find that in dysprosium ethylsulphate at temperatures between 3.0°K and 1.6°K the relaxation time varies as $\exp(\Delta/kT)$ with $\Delta/k = 23.6 \pm 2^\circ$. In this substance the ground state of the dysprosium ion is predominantly $J_z = \pm 9/2$, with excited states at 23.0° and 29.1° (Gramberg and Kahle, quoted by Meyer and Smith [2]) the lower of these states being predominantly $J_z = \pm 7/2$. It appears then that in this salt the statistical process is again the predominant relaxation mechanism. Similar results were obtained for ytterbium ethylsulphate, with $\Delta/k = 40 \pm 2^\circ$. Here we have no measured value for the energy of the first excited state, though the specific heat measurements of Meyer and Smith [2] would indicate a somewhat higher value than 40°.

The measurements on the other two salts showed a quite different temperature-dependence. Since the lowest excited states of the neodymium ion in the ethyl sulphate are estimated by Elliott and Stevens [3] to lie

¹ Supported in part by the U.S. Air Force Cambridge Research Centre through the European Office of A.R.D.C.

² National Science Foundation Postdoctoral Fellow.

at approximately 180° and 240° , the probability of phonon-induced transitions to these levels is comparatively small. There is no accurate information on the excited states of the erbium ion in the ethylsulphate; the lowest levels are believed to lie at about 70° above the ground state.

Preliminary measurements have been made on the field dependence of the relaxation time in the dysprosium salt. These have not been analysed in detail, but show a variation of the expected form.

1. FINN, C. B. P., R. ORBACH and W. P. WOLF, Communication to Colloque Ampère, Pisa, 1960.
 2. MEYER, H. and P. L. SMITH, *J. Chem. Phys. Solids*, 9, 285, 1959.
 3. ELLIOTT, R. J. and K. W. H. STEVENS, *Proc. Roy. Soc., A* 219, 387, 1953
-