

**Zeitschrift:** IABSE publications = Mémoires AIPC = IVBH Abhandlungen  
**Band:** 21 (1961)  
  
**Artikel:** Creep deflections in concrete and reinforced concrete columns  
**Autor:** Distefano, Jose Nestor  
**DOI:** <https://doi.org/10.5169/seals-18245>

### **Nutzungsbedingungen**

Die ETH-Bibliothek ist die Anbieterin der digitalisierten Zeitschriften. Sie besitzt keine Urheberrechte an den Zeitschriften und ist nicht verantwortlich für deren Inhalte. Die Rechte liegen in der Regel bei den Herausgebern beziehungsweise den externen Rechteinhabern. [Siehe Rechtliche Hinweise.](#)

### **Conditions d'utilisation**

L'ETH Library est le fournisseur des revues numérisées. Elle ne détient aucun droit d'auteur sur les revues et n'est pas responsable de leur contenu. En règle générale, les droits sont détenus par les éditeurs ou les détenteurs de droits externes. [Voir Informations légales.](#)

### **Terms of use**

The ETH Library is the provider of the digitised journals. It does not own any copyrights to the journals and is not responsible for their content. The rights usually lie with the publishers or the external rights holders. [See Legal notice.](#)

**Download PDF:** 15.05.2025

**ETH-Bibliothek Zürich, E-Periodica, <https://www.e-periodica.ch>**

# Creep Deflections in Concrete and Reinforced Concrete Columns

*Déformations dues au fluage de colonnes en béton et béton armé*

*Kriechdeformationen in Beton und Stahlbetonstützen*

JOSE NESTOR DISTEFANO

Professor, Argentine

## I. Introduction

Previous literature [1], [2], [3], [4] on creep deflections in columns was based on different models of linear viscoelastic material and all the papers seem to prove that indefinitely large deflections can be reached after an indefinitely long time, and failure occurs when the ultimate bending moment is reached.

Other papers [5], [6] show that for every  $P$  (axial force) between zero and the Euler's critic load, deflections converge towards a finite value when time tends to infinity.

This differences in conclusions can be explained because of the different models used for representing linear viscoelastic materials. In the present paper, the integral expression of Volterra's theory of hereditary phenomena [7] is used, which permits a great generality, because the differential expressions used to represent the viscoelastic bodies e.g., Maxwell, standard, etc. are but particular cases of the Volterra's integral expression. Moreover, by means of this representation it is possible to take into account, as closely as we want, reduction of creep due to the age of concrete.

In the present paper, deflections due to creep in symetrically reinforced concrete columns are studied. It is shown that creep deflections tend to a finite limit as  $t \rightarrow \infty$ , if, and only if, the axial load is not equal to or less than a certain value  $P^* < P_k$ , where  $P_k$  is the Euler's critic load. When  $P^* \leq P \leq P_k$ , deflections will reach infinitely large values for  $t \rightarrow \infty$ . The upper limit  $P^*$  of loads (below which only finite deflections are possible) depend, on the

asymptotic value of the specific creep strain — measured in the aged concrete —, on the inertia moment of the steel reinforcement and on the elastic modulus of both materials.

## II. Creep in Concrete

It is generally accepted that creep in concrete is proportional at every time to the applied stress, and that it verifies the superposition principle in the Boltzmann's sense, provided 30% to 50% of the rupture stress is not exceeded [8], [9], [10], [11], [12].

In this form, it is possible to represent the creep strain of a concrete element by means of the general integral expression of Volterra's theory of linear hereditary phenomena. Let  $\sigma(t)$  be the applied stress, variable with time  $t$ . Then it is possible to write the creep strain

$$\bar{\epsilon}(t) = \int_{\tau_0}^t \sigma(\tau) f(t, \tau) d\tau, \quad (1)$$

where  $\tau_0$  is the instant in which the stress is applied, and  $f(t, \tau)$  is the creep coefficient defined by

$$f(t, \tau) = -\frac{\partial}{\partial \tau} \bar{\epsilon}_0(t, \tau), \quad (2)$$

where  $\bar{\epsilon}_0(t, \tau)$  is the specific creep produced when a stress of 1 kg/cm<sup>2</sup> is applied at the instant  $\tau$ . The specific creep for different ages  $\tau$  of concrete can be found experimentally and the creep strain is well defined by mean of Eq. (1).

It is assumed that the instantaneous strain, produced when stress is applied, will obey Hooke's law, so that

$$\epsilon(t) = \frac{\sigma(t)}{E_b}, \quad (3)$$

where  $E_b$  is the elastic modulus of concrete.

## III. Integro-Differential Equations of Bending

If we consider that bending takes place only in a principal inertia plane and that sections, plain before bending, remain plain, the total strain can be expressed by

$$\epsilon(t) + \bar{\epsilon}(t) = \lambda(t) + \mu(t)z. \quad (4)$$

Eliminating  $\epsilon(t)$  between (3) and (4), and taking into account that in the zone occupied by the steel must be  $\bar{\epsilon}(t) = 0$ , stresses  $\sigma_b$  and  $\sigma_e$  in concrete and steel can be calculated by

$$\sigma_b(t) = E_b [\lambda(t) + \mu(t)z - \bar{\epsilon}(t)], \quad (5)$$

$$\sigma_e(t) = E_e [\lambda(t) + \mu(t)z]. \quad (6)$$

The conditions of static equilibrium when an axial load  $P$  and a bending moment  $M$  act in the cross section, are expressed by

$$P = \int_{A_b} \sigma_b dA_b + \int_{A_e} \sigma_e dA_e, \quad (7)$$

$$M = \int_{A_b} \sigma_b z dA_b + \int_{A_e} \sigma_e z dA_e, \quad (8)$$

where  $A_b$  and  $A_e$  are the concrete and steel areas, respectively. Substituting (5) and (6) in (7) and (8), these last take the form

$$P = \lambda E_b \bar{A} + \mu (E_b S_b + E_e S_e) - E_b \int_{\tau_0}^t f(t, \tau) d\tau \int_{A_b} \sigma_b(\tau) dA_b, \quad (9)$$

$$M = \mu E_b \bar{I} + \lambda (E_b S_b + E_e S_e) - E_b \int_{\tau_0}^t f(t, \tau) d\tau \int_{A_b} \sigma_b(\tau) z dA_b, \quad (10)$$

where  $\bar{\epsilon}(t)$  was replaced by its equivalent (1), and where

$$\begin{aligned} \bar{A} &= A_b + n A_e; & \bar{I} &= I_b + n I_e, \\ S_b &= \int_{A_b} z dA_b; & S_e &= \int_{A_e} z dA_e. \end{aligned}$$

From equilibrium Eqs. (7) and (8) and taking into account (6), it is then possible to calculate the following integrals

$$\begin{aligned} \int_{A_b} \sigma_b dA_b &= P - \lambda E_e A_e - \mu E_e S_e, \\ \int_{A_b} \sigma_b z dA_b &= M - \lambda E_e S_e - \mu E_e I_e. \end{aligned}$$

These integrals, substituted in (9) and (10), give the following equations

$$\begin{aligned} \lambda + \mu R + E_e \frac{A_e}{\bar{A}} \int_{\tau_0}^t \lambda f d\tau + E_e \frac{S_e}{\bar{A}} \int_{\tau_0}^t \mu f d\tau &= \frac{1}{E_b \bar{A}} [P + E_b \int_{\tau_0}^t P f d\tau], \\ \lambda R + \mu + E_e \frac{S_e}{\bar{I}} \int_{\tau_0}^t \lambda f d\tau + E_e \frac{I_e}{\bar{I}} \int_{\tau_0}^t \mu f d\tau &= \frac{1}{E_b \bar{I}} [M + E_b \int_{\tau_0}^t M f d\tau], \end{aligned} \quad (11)$$

where  $R = \frac{1}{\bar{A}} (S_b + n S_e).$

These equations are simplified if we choose the axis so that

$$S_b + n S_e = \bar{A} R = 0.$$

Moreover, in the present paper we will consider only the case in which the steel is symmetrically placed with respect to the bending axis. With this disposition, it will be  $S_e = 0$ , and the system (11) will be reduced to the following independent integral equations:



$$\lambda + E_e \frac{A_e}{\bar{A}} \int_{\tau_0}^t \lambda f(t, \tau) d\tau = \frac{1}{E_b \bar{A}} [P + E_b \int_{\tau_0}^t P f(t, \tau) d\tau], \quad (12)$$

$$\mu + E_e \frac{I_e}{\bar{I}} \int_{\tau_0}^t \mu f(t, \tau) d\tau = \frac{1}{E_b \bar{I}} [M + E_b \int_{\tau_0}^t M f(t, \tau) d\tau]. \quad (13)$$

We will suppose now that the column have a little initial eccentricity  $y_0(x)$ , so that the bending moment  $M$  can be expressed by

$$M = P[y(x, t) + y_0(x)]. \quad (14)$$

Substituting (14) in (12) and (13), and the curvature  $\mu$  by its approximate value  $\mu = -\frac{\partial^2 y}{\partial x^2}$  and considering that the axial  $P$  is constant with time, Eqs. (12) and (13) are modified in

$$\lambda + E_e \frac{A_e}{\bar{A}} \int_{\tau_0}^t \lambda f(t, \tau) d\tau = \frac{P}{E_b \bar{A}} [1 + E_b \bar{\epsilon}_0(t, \tau_0)], \quad (15)$$

$$\frac{P}{E_b \bar{I}} y + \frac{\partial^2 y}{\partial x^2} + \frac{1}{\bar{I}} \int_{\tau_0}^t \left( P y + E_e I_e \frac{\partial^2 y}{\partial x^2} \right) f(t, \tau) d\tau = -\frac{P}{E_b \bar{I}} y_0(x) [1 + E_b \bar{\epsilon}_0(t, \tau_0)]. \quad (16)$$

First, we will solve the integral-differential equation for deflections (16), and then we will solve Eq. (15).

#### IV. Solution of Equation (16)

To solve Eq. (16) we will suppose that it is possible to develop the functions  $y(x, t)$  and  $y_0(x)$  in series of functions  $\varphi_i(x)$

$$y_0(x) = \sum_1^{\infty} a_i \varphi_i(x), \quad (17)$$

$$y(x, t) = \sum_1^{\infty} b_i(t) \varphi_i(x), \quad (18)$$

where  $\varphi_i(x)$  are the eigen-functions of the differential equation

$$[\varphi_i'' + k_i \varphi_i]'' = 0, \quad (19)$$

whose first derivates  $\varphi_i'$  are orthogonal functions, *when conditions of free, or hinged, or built-in end are satisfied* [13]. By means of this property of orthogonality coefficients  $a_i$  are immediately calculated by

$$a_i = \frac{\int_0^l y_0'(x) \varphi_i'(x) dx}{\int_0^l [\varphi_i'(x)]^2 dx}.$$

With respect to coefficient  $b_i(t)$ , eliminating functions  $y(x, t)$  and  $\varphi_i(x)$  between Eqs. (16), (18) and (19), the following condition equations are obtained

$$b_i(t) + \beta_i \int_{\tau_0}^t b_i(\tau) f(t, \tau) d\tau = \frac{P}{k_i E_b \bar{I} - P} a_i [1 + E_b \bar{\epsilon}_0(t, \tau_0)], \quad (20)$$

where

$$\beta_i = E_b \frac{k_i E_e I_e - P}{k_i E_b \bar{I} - P}.$$

To solve the above integral equation, it is convenient to reduce a little the generality of function  $f(t, \tau)$  or what is the same, of the function  $\bar{\epsilon}_0(t, \tau)$ . It is noted that in materials like synthetic plastics or aged concrete, creep depends only on the difference of parameters  $t - \tau$  [14]; in this case, Eq. (20) can be rapidly solved by means of the Laplace's transformation, and the asymptotic properties of solutions can be easily investigated [15]. But in young concrete, creep depends not only on the difference  $t - \tau$ , but also on the age  $\tau$ . Aroutiounian [16] proposes to represent the specific creep with the function

$$\bar{\epsilon}_0(t, \tau) = \psi(\tau) F(t - \tau) \quad (21)$$

where  $\psi(\tau)$  is always positive and decreases monotonely towards the finite limit  $\psi(\infty) = \gamma_0$ , and it represents the damping of creep due to age. The function  $F(t - \tau)$  is also positive and monotonely grows towards an upper limit equal to unity, for great values of parameters  $t - \tau$ . Taking

$$\begin{aligned} \psi(\tau) &= \gamma_0 + \frac{C}{\tau}, \\ F(t - \tau) &= 1 - e^{-\delta(t - \tau)} \end{aligned} \quad (22)$$

and choosing convenient values of the constants  $\gamma_0, C, \delta$ , it is possible to follow as closely as we want, the creep of the concrete, with its dependence on age. The creep coefficient  $f(t, \tau)$  can be calculated by means of Eq. (2) and its value is in this case

$$f(t, \tau) = -\frac{\partial}{\partial \tau} [\psi(\tau) (1 - e^{-\delta(t - \tau)})]. \quad (23)$$

Substituting (23) in Eq. (20), and rewriting, we have

$$b_i(t) - \beta_i \int_{\tau_0}^t b_i(\tau) \psi'(\tau) d\tau + \beta_i \int_{\tau_0}^t b_i(\tau) (\psi' + \delta \psi) e^{-\delta(t - \tau)} d\tau = h_i(t, \tau_0). \quad (24)$$

where  $h_i(t, \tau_0)$  is the second member of Eq. (20).

Differentiations above equation with respect to  $t$

$$b_i'(t) + \beta_i \delta \psi(t) b_i(t) - \delta \beta_i \int_{\tau_0}^t b_i(\tau) (\psi' + \delta \psi) e^{-\delta(t - \tau)} d\tau = h_i'(t, \tau_0). \quad (25)$$

Eliminating the integral

$$\int_{\tau_0}^t b_i(\tau) (\psi' + \delta \psi) e^{-\delta(t - \tau)} d\tau$$

between Eqs. (24) and (25), and differentiating again with respect to  $t$ , the following differential equation is obtained

$$b_i''(t) + \delta [1 + \beta_i \psi(t)] b_i'(t) = 0 \quad (26)$$

with the following boundary conditions

$$\begin{aligned} b_i(\tau_0) &= h_i(\tau_0, \tau_0) = \frac{P a_i}{k_i E_b \bar{I} - P}, \\ b_i'(\tau_0) &= E_b \frac{P a_i}{k_i E_b \bar{I} - P} \psi(\tau_0) \delta \left( 1 - \frac{k_i E_e I_e - P}{k_i E_b \bar{I} - P} \right). \end{aligned} \quad (27)$$

The general solution of Eq. (26) is obtained by means of two successive integrations

$$b_i(t) = b_i(\tau_0) + b_i'(\tau_0) \int_{\tau_0}^t e^{-J_i(\xi)} d\xi, \quad (28)$$

where

$$J_i(t) = \delta \int_{\tau_0}^t [1 + \beta_i \psi(\tau)] d\tau.$$

Substituting for  $\psi(\tau)$  from (22), the integral becomes transformed into

$$J_i(t) = \delta (1 + \beta_i \gamma_0) (t - \tau_0) + \ln \left( \frac{t}{\tau_0} \right)^{\beta_i C \delta},$$

which substituted in (28) gives

$$b_i(t) = b_i(\tau_0) + b_i'(\tau_0) e^{\delta \tau_0 (1 + \beta_i \gamma_0)} \tau_0^{\beta_i C \delta} \int_{\tau_0}^t e^{-\delta (1 + \beta_i \gamma_0) \tau} \tau^{-\beta_i C \delta} d\tau. \quad (29)$$

Introducing the incomplete gamma function  $\Phi(\alpha, t)$  defined by

$$\Phi(\alpha, t) = \int_0^t e^{-\tau} \tau^{\alpha-1} d\tau.$$

Eq. (29) becomes

$$b_i(t) = b_i(\tau_0) + b_i'(\tau_0) e^{\nu_i \tau_0} \tau_0^{1-\alpha_i} \nu_i^{-\alpha_i} [\Phi(\alpha_i, \nu_i t) - \Phi(\alpha_i, \nu_i \tau_0)], \quad (30)$$

where

$$\begin{aligned} \alpha_i &= 1 - \beta_i C \delta, \\ \nu_i &= \delta (1 + \beta_i \gamma_0). \end{aligned}$$

## V. Convergence of Deflections

The integral that figures in Eq. (29) is convergent for  $t \rightarrow \infty$ , if, and only if,

- a)  $1 + \beta_i \gamma_0 > 0$ ,
- b)  $1 - \beta_i C \delta > 0$ ,

remembering the value of  $\beta_i$  given by Eq. (20), the first condition is verified if

$$0 \leq P < \frac{E_b \bar{I} k_m}{1 + E_b \gamma_0} (1 + E_b \gamma_0 \rho),$$

where  $k_m$  is the smaller eigenvalue of differential Eq. (19) and where  $\rho = \frac{n I_e}{\bar{I}}$ . But it is easy to show that  $E_b \bar{I} k_m$  is just Euler's critic load of the reinforced concrete column calculated in perfectly elastic range. Consequently, the above inequality can be written

$$0 \leq P < \frac{P_k}{1 + E_b \gamma_0} (1 + E_b \gamma_0 \rho). \quad (31)$$

With respect to condition (b) it can be expressed as follows:

$$E_b C \delta \frac{\rho P_k - P}{P_k - P} < 1. \quad (32)$$

Because  $\rho$  can be varied between zero and one, when  $\rho$  is placed in the interval

$$0 \leq \rho \leq \frac{P}{P_k}$$

the condition (32) is always verified, for every value of  $E_b C \delta$  coefficient. But, when  $\rho$  is in the interval (columns very much reinforced)

$$\frac{P}{P_k} < \rho \leq 1$$

condition (32) is verified if, and only if,

$$E_b C \delta < 1. \quad (33)$$

We are justified in assuming that this inequality is satisfied because a large number of experiments [8] show that generally the factor  $E_b C \delta$  does not exceed 0.5.

Once the conditions of convergence of functions  $b_i(t)$  are established, we will examine the deflections. These are given by (18).

From conditions of convergence of  $b_i(t)$  functions, we can conclude that

a) *When the axial load  $P$  is placed in the interval (31), deflections will tend to the following finite limit, for  $t \rightarrow \infty$*

$$y(x, \infty) \rightarrow \sum_1^{\infty} b_i(\tau_0) \varphi_i(x) + \sum_1^{\infty} b'_i(\tau_0) e^{\nu_i \tau_0} \tau_0^{1-\alpha_i} \nu_i^{-\alpha_i} [\Phi(\alpha_i, \infty) - \Phi(\alpha_i, \nu_i \tau_0)]. \quad (34)$$

b) *When the axial Load  $P$  is placed in the range*

$$\frac{P_k}{1 + E_b \gamma_0} (1 + E_b \gamma_0 \rho) \leq P < P_k \quad (35)$$

*the functions  $b_i(t)$ , and consequently the deflections, will tend to infinity for  $t \rightarrow \infty$ .*

Naturally, when  $P \geq P_k$ , large deflections will be produced instantaneously.

## VI. Stresses in Concrete and Steel

Having calculated functions  $b_i(t)$  by means of (30), curvature  $\mu$  is immediately calculated by means of

$$\mu(x, t) = - \sum_1^{\infty} b_i(t) \varphi_i''(x). \quad (36)$$

It is possible to calculate the function  $\lambda(t)$  by means of the integral Eq. (15). With a similar treatment given to integral Eq. (20), Eq. (15) reduces to the following differential equation

$$\lambda'' + \delta [1 + \theta \psi(t)] \lambda' = 0; \quad \theta = E_e \frac{A_e}{A} \quad (37)$$

associated with the following boundary conditions

$$\begin{aligned} \lambda(\tau_0) &= \frac{P}{E_b A}, \\ \lambda'(\tau_0) &= n \frac{P}{A} \psi(\tau_0) \delta \left( 1 + \frac{A_e}{A} \right). \end{aligned}$$

General solution of (37) is then obtained

$$\lambda(t) = \frac{P}{E_b A} \left[ 1 + E_e \psi(\tau_0) \delta \left( 1 + \frac{A_e}{A} \right) e^{\delta \tau_0 (1 + \theta \gamma_0)} \tau_0^{\theta C \delta} \int_{\tau_0}^t e^{-\delta (1 + \theta \gamma_0) \tau} \tau^{-\theta C \delta} d\tau \right]. \quad (38)$$

The conditions of convergence for  $t \rightarrow \infty$  of the integral are

$$\begin{aligned} 1 + \theta \gamma_0 &> 0, \\ 1 + \theta C \delta &> 0, \end{aligned}$$

which are always verified because  $\theta = E_e \frac{A_e}{A} \geq 0$ . Knowing  $\lambda$  and  $\mu$  by means of (36) and (38), the elastic stresses in the steel can be immediately calculated from

$$\sigma_e = E_e (\lambda + \mu z). \quad (39)$$

The stresses  $\sigma_b$  in concrete will be calculated in the following manner: we will calculate the bending moment  $M_b$  and the axial force  $P_b$  absorbed by the concrete only

$$\begin{aligned} M_b &= P(y + y_0) - \int_{A_e} \sigma_e z dA_e, \\ P_b &= P - \int_{A_e} \sigma_e dA_e \end{aligned}$$

and then we can apply the well know formula of Strength of Materials.

$$\sigma_b = \frac{P_b}{A_b} + \frac{M_b}{I_b} z.$$

## VII. Generalization of the Problem in the Case of the Beam-Column

Supposing a system of lateral loads are applied to the column, which produce a bending moment  $\mathfrak{M}(x)$  in the absence of the axial load  $P$ , then the total bending moment will be

$$M = P y(x, t) + P y_0(x) + \mathfrak{M}(x). \quad (40)$$

Taking 
$$\kappa(x) = y_0(x) + \frac{1}{P} \mathfrak{M}(x).$$

The previous developments remain unchanged if instead of coefficients  $a_i$  we take coefficients  $a_i^*$  given by the formula

$$a_i^* = \frac{\int_0^l \kappa'(x) \varphi_i'(x) dx}{\int_0^l [\varphi_i'(x)]^2 dx}.$$

Then the condition of convergence of deflections will not change.

## VIII. Discussion

In section V we have shown that deflections will tend to a finite limit with  $t \rightarrow \infty$ , if, and only if, the axial load belongs to the interval (31). While, when  $P$  is in the interval (35), the deflections will tend towards infinity for  $t \rightarrow \infty$ . These conclusions are based on the linear creep theory, which is valid only when the stresses in the concrete are not greater than 30% to 50% of the rupture stress. Experiments show that when the stresses are greater than this limit, creep is not linear, increasing more rapidly with increasing stresses [17]. For this reason, axial loads  $P$  placed in the interval (35), are always creep failure loads.

It is important to note that the amplitude of the interval of the safe loads (31), can be modified by varying the proportion of steel in the column. When the columns have no steel, that is  $\rho = 0$ , the interval (31) is reduced to

$$0 \leq P < \frac{P_k}{1 + E_b \gamma_0}$$

while, when the column is reduced (by increasing the proportion of steel) to a purely steel one, then  $\rho = 1$ , and the interval (31) is enlarged to

$$0 \leq P < P_k$$

this naturally corresponds to a purely elastic column.

We can see now in a particular case the influence of a steel reinforcement of 3.33% in a rectangular concrete column. Suppose that the reinforcement is formed by 4 steel bars placed in the corner of the rectangle, with this dis-

position, and considering  $n=10$ ,  $\rho$  has the value  $1/2$ . We suppose now that factor  $E_b \gamma_0 = 2$ . The range of the safe load (31) of a column without steel will be

$$0 \leq P < \frac{1}{3} P_k.$$

While for the same column reinforced with 3.33% of steel, the range will be

$$0 \leq P < \frac{2}{3} P_k.$$

That is to say, the amplitude of the range was duplicated.

Finally, we wish to mention the creep-buckling experiments carried out by RENÉ PERZO [18], which seem to confirm the previous criterion. Plain concrete plates of 250/4/50 cm, built-in at the ends, were axially loaded at the age of 7 days. These tests showed that the time of rupture by creep, increases quickly when load is decreased, and that loads below  $0.30 P_k$  are not capable of producing rupture.

On the other hand, creep tests made at the same time, on concrete aged 21 days, showed that factor  $\frac{1}{1 + E_b \gamma_0}$  has the value 0.33.

### Notation

$P$	= Axial load
$P_k$	= Euler's critical load
$M$	= Bending moment
$\epsilon$	= Elastic strain
$\bar{\epsilon}$	= Creep strain
$\bar{\epsilon}_0$	= Specific creep produced by $\sigma = 1 \text{ k cm}^{-2}$
$\sigma$	= Stress
$t$	= Time
$\tau$	= Age of concrete
$E_e$	= Elastic modulus of steel
$E_b$	= Elastic modulus of concrete
$n$	= $\frac{E_e}{E_b}$
$\lambda$	= Shortening of the axis of the column
$\mu$	= Increment of curvature of the axis of the column, referred to the unloaded incurved position
$z$	= Ordinate of a generic point of the cross section with respect to the neutral axis
$A_e$	= Steel area
$A_b$	= Concrete area
$\bar{A}$	= $A_b + n A_e$

$$\begin{aligned}
 I_e &= \int_{A_e} z^2 dA_e \\
 I_b &= \int_{A_b} z^2 dA_b \\
 \bar{I} &= I_b + n I_e \\
 y_0(x) &= \text{Initial deflection of the column axis} \\
 y(x, t) &= \text{Deflections of the column axes with respect to the unloaded incurred positions} \\
 \rho &= \frac{n I_e}{\bar{I}} \\
 \Phi(\alpha, t) &= \int_0^t e^{-\tau} \tau^{\alpha-1} d\tau = \text{Incomplete Gamma function}
 \end{aligned}$$

### Bibliography

1. KEMPNER and POHLE. On the Nonexistence of a Finite Critical Time for Linear Viscoelastic Columns, *Journal Aeronautical Sciences*, Vol. 20, No. 8, pp. 572, August, 1953.
2. LIBOVE, CHARLES. Creep Buckling of Column. *Journal Aeronautical Sciences*, V. 19, No. 7, pp. 459, July, 1952.
3. HILTON, HARRY. Creep Collapse of Viscoelastic Columns with Initial Curvatures. *Journal Aeronautical Sciences*, Vol. 19, No. 12, pp. 844, December, 1952.
4. HOFF, N. J. A Survey of the Theories of Creep Buckling. *Proceedings of the Third U. S. National Congress of Applied Mechanics*, Pergamon Press, 1958.
5. LEVI, FRANCO. Fluage, plasticité, precontrainte. Dunod 1953.
6. LEVI, FRANCO. Instabilità elastico-viscosa in campo iperstatico. *La ricerca scientifica*, anno 29<sup>o</sup>, No. 7, July 1959.
7. VOLTERRA, V. Leçon sur les fonctions des lignes. Paris 1913.
8. MAMILLAN. A Study of the Creep of Concrete. *Bulletin RILEM*, No. 3, July, 1959.
9. FREUDENTHAL and ROLL. Creep and creep recovery of concrete under high compressive stress. *Journal of the American Concrete Institute*, June, 1958.
10. WEIL, G. Influence des dimensions et des contraintes sur le retrait et le fluage du Béton. *Bulletin RILEM*, No. 3, July, July, 1959.
11. AROUTIOUNIAN, N. KH. Applications de la théorie du fluage. Ed. Eyrolles, Paris, 1957.
12. ROSS, A. D. Creep under variable stress. *Journal of the American Concrete Institute*, March, 1958.
13. BLEICH, F. Buckling Strength of Metal Structures. McGraw-Hill, 1952.
14. DISTEFANO, J. N. Base sperimentale per una teoria sul comportamento di strutture visco-elastiche lineari. — *La Ricerca Scientifica*, Anno 30<sup>o</sup>, No. 1, January, 1960.
15. DISTEFANO, J. N. Sulla stabilità in regime visco-elastico a comportamento lineare (2 notes). — *Rendiconti Accademia Naz. dei Lincei*, fasc. 5 and 6, Serie VIII, Vol. XXVII, November, 1959.
16. AROUTIOUNIAN, N. KH. Loc. cit. Pag. 44.
17. FREUDENTHAL and ROLL. Loc. cit.
18. PERZO, RENÉ. Palais du Centre National des Industries et des Techniques. Essais et mesures — *Travaux*, June 1959, Pag. 374.



### Summary

In the present paper, deflections due to creep in reinforced concrete columns with symmetrical steel reinforcement are studied. It is shown that creep deflections tend to a finite limit for  $t \rightarrow \infty$ , if, and only if, axial load is not equal or smaller than a certain value  $P^* < P_k$ , where  $P_k$  is the Euler's critic load. When  $P^* \leq P \leq P_k$ , deflections will reach infinitely large values for  $t \rightarrow \infty$ . The upper limit  $P^*$  of loads (below which only finite deflections are possible) depends on the asymptotic value of the specific creep, measured in the aged concrete, on the inertia moment of the steel reinforcement and on the elastic modulus of both materials.

### Résumé

L'auteur étudie les déformations dues au fluage de colonnes en béton armé à armature symétrique. Pour  $t \rightarrow \infty$ , les déformations dues au fluage ne tendent vers une valeur finie que si la charge axiale n'atteint pas une certaine valeur  $P^* < P_k$ ,  $P_k$  désignant la charge critique d'EULER. Lorsque l'on a  $P^* \leq P \leq P_k$ , les déformations atteindront des valeurs infinies pour  $t \rightarrow \infty$ . La limite supérieure  $P^*$  (au-dessous de laquelle seules des déformations finies sont possibles) dépend de la valeur limite du fluage spécifique, mesurée sur le béton vieilli, du moment d'inertie de l'armature et du module d'élasticité des deux matériaux.

### Zusammenfassung

Im vorliegenden Beitrag werden die Kriechverformungen von symmetrisch bewehrten Stahlbetonstützen untersucht. Für  $t \rightarrow \infty$  zeigt sich, daß die Kriechdeformation einem endlichen Grenzwert zustrebt, solange und nur solange als die zentrische Belastung kleiner als ein bestimmter Wert  $P^* < P_k$  ist, wo  $P_k$  die Eulersche Knicklast bedeutet. Liegt  $P$  zwischen  $P^*$  und  $P_k$  ( $P^* \leq P \leq P_k$ ), so wächst für  $t \rightarrow \infty$  die Kriechdeformation ins Unendliche. Die obere Lastgrenze  $P^*$  (unterhalb welcher nur endliche Deformationen eintreten können) wird bestimmt durch den Endwert des spez. Kriechmaßes (an gealtertem Beton gemessen), durch das Trägheitsmoment der Bewehrung und den Elastizitätsmodul beider Baustoffe.