

# Indirect loading and indirect supporting in high-strength concrete beams

Autor(en): **Fernandes, Gilson Battiston**

Objektyp: **Article**

Zeitschrift: **IABSE reports = Rapports AIPC = IVBH Berichte**

Band (Jahr): **83 (1999)**

PDF erstellt am: **22.07.2024**

Persistenter Link: <https://doi.org/10.5169/seals-62836>

## **Nutzungsbedingungen**

Die ETH-Bibliothek ist Anbieterin der digitalisierten Zeitschriften. Sie besitzt keine Urheberrechte an den Inhalten der Zeitschriften. Die Rechte liegen in der Regel bei den Herausgebern.

Die auf der Plattform e-periodica veröffentlichten Dokumente stehen für nicht-kommerzielle Zwecke in Lehre und Forschung sowie für die private Nutzung frei zur Verfügung. Einzelne Dateien oder Ausdrucke aus diesem Angebot können zusammen mit diesen Nutzungsbedingungen und den korrekten Herkunftsbezeichnungen weitergegeben werden.

Das Veröffentlichen von Bildern in Print- und Online-Publikationen ist nur mit vorheriger Genehmigung der Rechteinhaber erlaubt. Die systematische Speicherung von Teilen des elektronischen Angebots auf anderen Servern bedarf ebenfalls des schriftlichen Einverständnisses der Rechteinhaber.

## **Haftungsausschluss**

Alle Angaben erfolgen ohne Gewähr für Vollständigkeit oder Richtigkeit. Es wird keine Haftung übernommen für Schäden durch die Verwendung von Informationen aus diesem Online-Angebot oder durch das Fehlen von Informationen. Dies gilt auch für Inhalte Dritter, die über dieses Angebot zugänglich sind.



## Indirect Loading and Indirect Supporting in High-Strength Concrete Beams

**Gilson Battiston FERNANDES**  
Professor  
Universidade Estadual de Campinas  
Campinas, SP - Brazil

Gilson Battiston Fernandes, born in 1946, received his civil engineering, M.Sc. and Doctor degrees from Universidade de São Paulo, Brazil

### Abstract

In concrete structures, most frequently, the loads and reactions are applied on the top and the bottom of the beams, respectively. These are said to be directly loaded and directly supported beams. However, situations are found in which the beams are loaded or supported by intersecting beams so that the load transfer is by shear rather than by bearing on the top or the bottom surface. These are referred to as indirectly loaded or indirectly supported beams.

The experimental investigations conducted during the past decades with normal-strength concrete beams showed that a tie shall be provided at the joint between these beams which is responsible for transferring the mutual reaction from the supported beam to the supporting beam. This transfer is accomplished by a reinforcement made up by stirrups referred to as hanger reinforcement.

This abstract is concerned with indirect loading and indirect supporting in high-strength concrete beams and reports the results of experimental investigation conducted by *Ribeiro* (1), under direction of the author, using horizontal T-shaped specimens. The specimens were B1-L and B1-R with shear span-to-depth ratio  $a/d = 1.89$  and C1-R with shear span-to-depth ratio  $a/d = 3.92$ . The beams were designed to fail in flexure. The flexural strength was given by the supporting beam. The predicted ultimate load was  $2F_u = 140\text{kN}$  and the corresponding mutual reaction was  $A_u = 1.2 F_u = 84\text{kN}$ . The specimen concrete average compressive strength at the age of the tests was about 80MPa.

The hanger reinforcement in specimen B1-L was made up by one 5.0mm diameter stirrup in the supported beam (beam B) and four 4.2mm diameter stirrups in the supporting beam (beam 1) arranged within  $h/2$  of the center of the intersection of the beams. This reinforcement could hang up 144% of the predicted ultimate mutual reaction: 34% for the stirrup in beam B and 110% for the stirrups in beam 1. The stirrup in the supported beam was responsible to hang 24% of the effective mutual reaction and those in the supporting beam were responsible to hang 76% of the effective mutual reaction. The two stirrups in the common volume could hang 55% of the predicted ultimate mutual reaction and were responsible to hang 38% of the effective mutual reaction. The hanger reinforcements in specimens B1-R and C1-R were made up by one 8.0mm diameter and two 6.3mm diameter stirrups placed at the common volume of the beams. This reinforcement could hang 137% of the predicted ultimate mutual reaction and was responsible to hang the full load transferred.

The tests showed that, initially, the load transfer is by shear over the depth of the beams. After cracking, the cracks produced by the principal tensile stresses in the supported beam follow the principal compressive stress trajectories. The inclined cracks in the supported beam give rise to a compressive stress field which acts as struts in a truss-like system. The stirrups crossing the cracks

play the role of ties in the web. The load on the supported beam is transferred to the tensile chord of the supporting beam by the last strut in the supported beam.

The tests showed that the supporting beam is initially uncracked while the load transfer is by shear. After cracking, the cracks produced by the principal tensile stresses give rise to a fan-like crack pattern similar to that known for directly loaded beams. At late load stages, horizontal cracks appear over the web of the supporting beam indicating a tie-like behaviour of the hanger reinforcement.

In specimen B1-L, at ultimate load  $2F_u = 170\text{kN}$  the mutual reaction was  $A_u = 102\text{kN}$ . At this load, the four stirrups in the supporting beam were hanging up  $79.3\text{kN}$  ( $0.77A_u$ ) and the single stirrup in the supported beam was hanging up  $23.6\text{kN}$  ( $0.23A_u$ ). At the same load the two stirrups in the common volume of the beams were hanging up  $47.7\text{kN}$  ( $0.46A_u$ ) and the next two were hanging up  $31.6\text{kN}$  ( $0.31 A_u$ ). The two stirrups in the common volume of the beams started yielding at a load  $2F = 160\text{kN}$  and one of the next two had started yielding at  $2F = 150\text{kN}$ . At these late load stages horizontal cracks appeared on the web of the supporting beam at the intersection of the beams due to stretching of the hanger reinforcement. At the same time a fan-like crack surface started to outline in the web of the supporting beam at the intersection of the beams. This crack surface was bounded by wide inclined cracks due to large yield strains in the hanger reinforcement. At a load  $2F = 175\text{kN}$ , just after the compressive chord had initiated crushing, the bottom of the supporting beam was suddenly pushed downward. This fact enhances that this hanger reinforcement did not provide effective support for the bottom of the supporting beam at the intersection of the beams, even though this reinforcement could hang up 119% of the effective mutual reaction: 28% for the stirrup in the supported beam and 91% for the stirrups in the supporting beam. This is because the hanging stirrups placed farther from the intersection are not as efficient as those in the common volume of the beams. The stirrups in the supporting beam were able to hang up only  $0.77A_u$  ( $0.46A_u$  for the stirrups in the common volume of the beams and  $0.31 A_u$  for those in outside) and needed the help from the stirrup in the supported beam to hang up the missing  $0.23A_u$ .

In specimen B1-R, at ultimate load  $2F_u = 170\text{kN}$  the mutual reaction was  $A_u = 102\text{kN}$ . At this load, the three stirrups were hanging up  $106.7\text{kN}$ . This load is approximately equal to  $A_u$ . These stirrups started yielding at a load  $2F = 160\text{kN}$ . At the late load stages, the same horizontal cracks and the same fan-like crack pattern appeared on the web of the supporting beam but no pushing-down failure occurred. The hanger reinforcement placed at the common volume of the beams was efficient up to failure of the specimen.

In specimen C1-R, at ultimate load  $2F_u = 160\text{kN}$  the mutual reaction was  $A_u = 96\text{kN}$ . At this load the three stirrups were hanging up  $100.4\text{kN}$ . This load is approximately equal to  $A_u$ . These stirrups reached yielding at failure of the specimen. The hanger reinforcement placed at the common volume of the beams once more was efficient up to failure of the specimen when the supported beam failed in shear tension.

## Reference

- [1] Ribeiro, F. C. V., *Apoio Carregamento Indiretos em Vigas de Concreto de Alta Resistencia*, Dissertação de Mestrado, Faculdade de Engenharia Civil - UNICAMP, Campinas-SP, Brasil, 1999.