Zeitschrift:	Schweizerische mineralogische und petrographische Mitteilungen = Bulletin suisse de minéralogie et pétrographie		
Band:	55 (1975)		
Heft:	1		
Artikel:	An occurence of bjarebyite in the Buranga pegmatite, Rwanda		
Autor:	Knorring, Oleg von / Fransolet, André-Mathieu		
DOI:	https://doi.org/10.5169/seals-43060		

Nutzungsbedingungen

Die ETH-Bibliothek ist die Anbieterin der digitalisierten Zeitschriften auf E-Periodica. Sie besitzt keine Urheberrechte an den Zeitschriften und ist nicht verantwortlich für deren Inhalte. Die Rechte liegen in der Regel bei den Herausgebern beziehungsweise den externen Rechteinhabern. Das Veröffentlichen von Bildern in Print- und Online-Publikationen sowie auf Social Media-Kanälen oder Webseiten ist nur mit vorheriger Genehmigung der Rechteinhaber erlaubt. <u>Mehr erfahren</u>

Conditions d'utilisation

L'ETH Library est le fournisseur des revues numérisées. Elle ne détient aucun droit d'auteur sur les revues et n'est pas responsable de leur contenu. En règle générale, les droits sont détenus par les éditeurs ou les détenteurs de droits externes. La reproduction d'images dans des publications imprimées ou en ligne ainsi que sur des canaux de médias sociaux ou des sites web n'est autorisée qu'avec l'accord préalable des détenteurs des droits. <u>En savoir plus</u>

Terms of use

The ETH Library is the provider of the digitised journals. It does not own any copyrights to the journals and is not responsible for their content. The rights usually lie with the publishers or the external rights holders. Publishing images in print and online publications, as well as on social media channels or websites, is only permitted with the prior consent of the rights holders. <u>Find out more</u>

Download PDF: 09.07.2025

ETH-Bibliothek Zürich, E-Periodica, https://www.e-periodica.ch

An Occurrence of Bjarebyite in the Buranga Pegmatite, Rwanda

By Oleg von Knorring*) and André-Mathieu Fransolet**)

With 2 figures and 5 tables in the text

Abstract

A second occurrence of bjarebyite, Ba $(Mn, Fe)_2$ $(Al, Fe)_2$ $(PO_4)_3$ $(OH)_3$ is described from Buranga pegmatite in Rwanda. This rare pegmatitic phosphate is closely associated with bertossaite, trolleite, apatite and lazulite.

The monoclinic unit cell dimensions, calculated from the powder pattern data, are: a = 9.103, b = 12.204, c = 4.959 Å and $\beta = 100^{\circ} 28'$ with Z = 2. Specific gravity is 3.90. Complete chemical analyses are given. The optical properties are: $\alpha = 1.724$, $\beta = 1.727$, $\gamma = 1.749$ and $2V = (+) 38^{\circ}$. The pleochroism is strong.

An infrared spectrum is given and briefly discussed.

Introduction

Buranga is noted for its exceptional variety of phoshate minerals which have been described by THOREAU et al. (1950–1957), ALTMANN (1961) and GALLACHER and GERARDS (1963). During four brief visits to this pegmatite area between 1964–1969, specimens were collected mainly for a comparative study in connection with pegmatite investigations in south-west Uganda. As a result of laboratory examination many rare minerals including four new phosphates have been noted. (VON KNORRING and HORNUNG, 1965, VON KNORRING and MROSE, 1966 and VON KNORRING, 1965, 1969, 1970, 1972, 1973.)

The Buranga pegmatite is situated about 0.5 km north of the Minétain company's headquarters at Gatumba ($29^{\circ} 31' \text{ E.}, 1^{\circ} 55' \text{ S.}$), some 50 km south of the administrative town of Ruhengeri in northern Rwanda. The rocks in this area belong to the Burundian system, comprising schists, quartzites, amphibolites and often dome-like granitic intrusives; they have a northerly

^{*)} Department of Earth Sciences, The University of Leeds, U.K.

^{**)} Institut de Minéralogie, Université de Liège, Belgium.

trend and are continous with the Karagwe-Ankolean rocks on the Uganda side of the border to the north. Granite pegmatites are of common occurrence and many have been mined for cassiterite in the past.

The Buranga occurrence is dominated by a NNW-striking quartz core, some 10 metres wide, in the southern part of pegmatite. In relation to the main quartz core the pegmatite is asymmetrical and is less well developed on the eastern side where it is in contact with a tourmalinized amphibolite; westwards the pegmatite passes gradually into a pegmatitic granite. There is a marked zoning around the quartz core which contains conspicuous lathshaped voids after giant spodumene crystals – a characteristic feature of many pegmatites in northern Rwanda and adjoining parts of south-west Uganda. Nodules and aggregates of phosphate minerals, some of gigantic proportions, are commonly observed within the quartz core or along the core margin. Next to the core there is a zone of albite and muscovite, partly kaolinized. Pockets of beryl and occasional aggregates of manganotantalite have been found in this zone, in addition to zircon, microlite and some uraniferous minerals.

A pistachio – to dark-green phosphate (now bjarebyite, MOORE et al. 1973) was observed at Buranga in 1965 and was subsequently identified by Miss MARY E. MROSE of the U.S. Geological Survey in Washington, who was then investigating an identical mineral found at the Palermo and Smith mines in New Hampshire.

Phosphate mineralization

The phosphate minerals in the Buranga pegmatite may be divided into three major associations as follows:

- 1. Manganese-iron nodules containing lithiophilite, heterosite-purpurite, ferrisicklerite, alluaudite, barian arrojadite, tavorite, barbosalite, lipscombite, frondelite, strengite, metastrengite, stewartite, bermanite and a mitridatite-like mineral.
- 2. Amblygonite (montebrasite) with minor lazulite (scorzalite), apatite, eosphorite and berlinite.
- 3. Aggregates containing variable amounts of lazulite (scorzalite), trolleite, bertossaite, amblygonite, brazilianite, augelite, with some apatite, bjarebyite, crandallite, wavellite, wardite and three new fibrous phosphates under investigation.

Muscovite and quartz may be present in these associations.

Paragenesis

Bjarebyite belongs to the third major assemblage of the phosphate minerals from the Buranga pegmatite that VON KNORRING (1970) distinguished.

This very complex phosphates association is mainly characterized by abundance of aluminium.

VON KNORRING (1969, 1970 and 1972) noted many species in it: amblygonite, trolleite, brazilianite, lazulite, augelite, berlinite, bertossaite with crandallite and wavellite. Quartz, apatite and muscovite also occur in the association.

Bjarebyite is pistachio-or dark-green in colour, striated and rather like tournaline in appearance. It is found intimately intergrown with bertossaite, though it is usually confined to small cavities, lined with quartz and fibrous apatite, in trolleite or bertossaite.

Under the microscope, this Ba-bearing phosphate appears in hypidiomorphic forms, frequently associated with quartz and a blue phosphate of the lazulite-scorzalite series. Sometimes, it shows an interstitial structure with this blue phosphate, in trolleite.

Crystallography

Single-crystal X-ray data

Rotation and Weissenberg photographs were obtained from a short, striated, prismatic crystal of bjarebyite from Buranga pegmatite, using nickel filtered copper radiation.

The diffraction data show monoclinic symmetry, compatible with space group P 2_1 and P $2_1/m$.

The recent determination by MOORE et al. (1973) confirms $P 2_1/m$ as the correct space group.

Preliminary cell parameters were obtained from measurements of these films. They were used to obtain the refined cell data from the powder diffractogram.

X-ray powder diffraction data

A diffractogram of bjarebyite was recorded on a Philips' diffractometer with an internal standard of oxammite (A.S.T.M. 14-801), using Ni-filtered copper radiation (CuK_{α} = 1.5418 Å).

Powder data are listed in table I where patterns of bjarebyite from Palermo mine are also listed for comparison.

The unit cell dimensions were computed with the least-squares refinement FORTRAN program of Cox (1967). The results are compared in table II with those recently reported by MOORE et al. (1973). The unit cell dimensions of bjarebyite from Buranga are greater and this seems to be related to the higher MnO amount in the formula (table IV).

Table	I.	X-ray	powder	data	for	bjarebyite

	Buranga (this repor	t)	Palermo) (MOORE e	et al., 1973)
$\mathbf{I}/\mathbf{I_0}$	d (Å)obs	hkl	d (Å)calc	$\mathbf{I}/\mathbf{I_0}$	d (Å)	hkl
100	8.952	100	8.952	7	8.81	100
5	7.237	110	7.218			
5	6.096	020	6.102			
15	5.042	120	5.042	4	4.97	120
15	4.649	$10\overline{1}$	4.651	2	4.59	101
15	4.529	011	4.528	4	4.47	011
5	4.473	200	4.476	-		
10	4.201	210	4.202	1	4.124	210
20	3.607	220	3.609	2	3.564	$\frac{220}{2}$
10	3.482	211	3.491	1	3.447	211
5	3.336	121	3.339	1	3.295	121
80	3.122	031	3.124	2	3.090	031
05	0.070	$\frac{221}{107}$	3.128	0	0.004	221
35	3.058	131	3.062	3	3.024	131
	B 000	040	3.051			
10	3.009	230	3.010		2.010	011
40	2.943	211	2.945	4	2.910	211
45	2.896	310	2.899	2	2.852	310
15	2.846	$131 \\ 0.01$	2.848	2	2.811	131
1	2.778	301	2.780	-	0.001	221
40	2.710	311	2.710	7	2.081	221
30	2.080	320	2.081	3	2.043	320, 311
1	2.580	041	2.580	1	0 514	1.41
10	2.550	141	2.001	1	2.014	141
10	2.019	103	2.021	2	2,490	321
10	2.410	102	2.409	2	2.444	102
10	2.432	231	2.432	1	2.413	002
10 5	2.400	330	2.400	1	2.377	330
10	2.310	011 015	2.210	1	2.310	202
10	2.201	400	2.200	4	2,201	212
20	2.230	201	2.200	9	9 1 7 7	410
20	2.201	410	2.202	2	2.177	410
15	9 106	401	2.201			
10	2.150	151	2.130	2	9 1 2 7	151
10	2.100	411	2.101	9	4.107	101
5	2 1 3 8	250	2.150			
5	2.130	340	2.140			
10	2.102	132	2.100	۲.	2 000	199
10	2.100	420	2.112	1	2.000	122
5	2.077	151	2.082			
15	2.057	341	2.052 2.055			
15	2.052	312	2.053	2	2 039	312
15	2.032	060	2.034	10	2.010	060. 232
15	2.027	25T	2.028		2.010	000, 202
10	2.014	$\overline{23\overline{2}}$	2.019			
5	1.987	160	1.983			
10	1.965	212	1.968	2	1.956	132
		132	1.970			
1	1.927	43T	1.928			
5	1.894	222	1.896	2	1.880	222
5	1.863	$16\overline{1}$	1.864	-		
5	1.817	421	1.820	1	1.786	4 02
		161	1.812	_		1. The State of State
4 0	1.790	500	1.790	1	1.759	500. 412
		232	1.791			
		50T	1.789			
30	1.786	44 Ī	1.779			

Bjarebyite in the Buranga Pegmatite

Buranga (this report)			rt)	Palermo	o (Moore e	t al., 1973)
$\mathbf{I}/\mathbf{I_0}$	d (Å)obs	hkl	d (Å)cale	I/I_0	d (Å)	hkl
10	1.775	$26\overline{1}$	1.776			
10	1.770	510	1.771	1	1.733	510
		$51\overline{1}$	1.770			
1	1.740	302	1.740			
5	1.718	520	1.718	1	1.702	$\overline{3}42$
		$52\overline{1}$	1.717			
5	1.696	351	1.697	1	1.681	351
5	1.680	360	1.681			
5	1.676	322	1.673			
5	1.671	242	1.669	1	1.659	$\overline{2}52$
5	1.666	$43\overline{2}$	1.663			
5	1.636	530	1.639	2	1.624	530
		$53\overline{1}$	1.638			
5	1.632	$17\overline{1}$	1.633			
		$45\overline{1}$	1.630			
5	1.616	441	1.617	2	1.600	441
10	1.588			2	1.578	501
5	1.565			3	1.556	$\overline{1}62$
10	1.541					
10	1.538			3	1.528	$\overline{5}14$
10	1.508				2	
15	1.502			5	1.495	$033,\overline{6}01$
10	1.477					
10	1.473					

Table II. Unit-cell parameters for bjarebyite

	Buranga (this report)	Palermo (Moore et al., 1973)
a b	$9.103 \pm 0.003 ~{ m \AA}$ $12.204 \pm 0.004 ~{ m \AA}$	8.930 Å 12.073 Å
c B	4.959 ± 0.002 Å 100° 28' + 1'	$4.907 \ { m \AA}$ 100.15°
v Space group	$542\pm 2 \text{ Å}^{3}$	521.8 Å ³ P 2 /m
Z	2^{10} (24° C)	$\frac{1}{2}$
G (calc)	3.924	$\frac{5.55 \pm 0.02}{4.02}$

Optical properties

Bjarebyite is biaxial positive. The refractive indices, measured in sodium light and determined with Cargille oils by the double variation method, are $\alpha = 1.724$, $\beta = 1.727$ and $\gamma = 1.749$ all values are accurate to ± 0.001 .

Birefringence, as observed with the Berek's compensator, is 0.022 and $(\gamma - \alpha) = 0.025$. The optic axial angle is (+) 38°, measured conoscopically on the universal stage. This value compares with $(+40^{\circ} 56')$, calculated from refractive index data, and lies within the limits of error of the refractive indices as determined.

A strong pleochroism is observed:

- Z, colourless to pale brownish yellow,
- Y, brownish green,
- X, apple or olive green.

Extinction angle between Z and c is 8° by universal-stage measurements and 7° as observed in thin section.

Y is assumed to be parallel to b and Z seems to lie in (010) in the acute angle β . Sections more or less normal to Z show strong dispersion (r < v) and two perfect cleavages, probably (010) and (100) (MOORE et al. 1973) (fig. 1).

These results are compared in table III with those obtained by MOORE et al. (1973). The difference between the optical data cannot be explained by chemical differences alone, in particular by the ratio Mn/Fe.



Fig. 1. Bjarebyite. Section nearly normal to Z showing two cleavages. Polarized crossed light.

Table III. Optical data for bjarebyite

	Buranga (this report)	Palermo (Moore et al., 1973)
α	1.724	1.692
β	1.727	1.695
γ	1.749	1.710
$\gamma - \alpha$	0.025	0.018
$2 V_{obs}$	$(+) 38^{\circ}$	(+) 35°
$2 V_{calc}$	$(+) 40^{\circ} 56'$	
$\mathbf{Z} \wedge c$	8°	
Pleochroism	strong	weak
	X = apple green	
	$\mathbf{Y} = \mathbf{brownish}$ green	
	$ m Z~=\pm~colourless$	
r	< v	\gg v

Chemical analysis

The results of two chemical analyses are given in table IV and are compared with those performed with electron microprobe by MOORE and al. (1973).

Table IV. Chemical analyses of bjarebyite

	1	2	2	4	5
$P_{2}O_{5}$		32.74	32.5	32.96	0.190
$A\tilde{l}_2\tilde{O}_3$	13.43	13.33	12.9	13.25	0.214
Fe ₂ O ₃		3.74	2.8	3.30	0.290
FeÕ	8.67	5.54	6.2	5.94	0.187
MnO	9.56	15.84	15.8	15.98	0.191
MgO			_		
BaO	23.69	23.35	23.9	23.87	0.127
SrO	1.57				
H,O	20. 24. 02 	4.81	4.5	4.70	0.340
Insol.		0.30	0.4		
Total		99.65	99.0	100.00	

1. Bjarebyite from Palermo mine. Oxides calculated from Moore' results (1973).

Analyst: O. VON KNORRING
 VON KNORRING (1973)
 Bjarebyite from Buranga pegmatite.
 Mean of the two analyses (2 and 3).

5. Specific refractive energies (Larsen and Berman, 1934).

The mean of the two analyses (4), the measured specific gravity 3.90 and the unit cell volume 542 Å³ suggest a cell content Z = 2 and a formula of

 $Ba(Mn_{1.45}Fe_{0.53}) (Al_{1.67}Fe_{0.28}) (PO_4)_{2.97} (OH)_{2.90} 0.22 H_2O$

or an idealised formula of

 $Ba(Mn, Fe)_2 (Al, Fe)_2 (PO_4)_3 (OH)_3$ with $Mn : Fe = 2.74 (\simeq 3: 1)$.

The calculated specific gravity 3.924 is in good agreement with G. meas. = 3.90.

The mean index of refraction, calculated by the Gladstone and Dale rule (IV, 5) from the mean of the two analyses is 1.735, compared to the mean measured index of 1.733.

Infrared absorption spectrum

The IR spectrum was recorded with a Beckman IR-12 spectrophotometer in the 200 cm^{-1} -4000 cm^{-1} region. The sample was prepared with 2 or 3 mg of bjarebyite diluted in pressed tablets of KI.

The infrared absorption spectrum of bjarebyite is given in figure 2. The wavenumber in cm^{-1} and the characteristics of the peaks are given in table V.



Fig. 2. Infrared absorption spectrum of bjarebyite.

Table V. Infrared absorption bands of bjarebyite

Wavenumber (cm ⁻¹)	Wavenumber (cm ⁻¹)
225 s	$582 \mathrm{w}$
$275 \mathrm{~m~b}$	612 s
313 s b	655 m
355 s	$871 \mathrm{sb}$
384 w	964 s
$435 \mathrm{sh}$	1015 m b
452 s	1050 w b
472 w	1085 w b
491 m	1133 m b
513 w	1187 s
$535 \mathrm{sh}$	3250 s b
545 s	3520 s
568 m	3540 s

s strong, m medium, w weak, b broad, sh shoulder

For the 200 cm⁻¹–700 cm⁻¹ region assignments of absorption peaks are very difficult and the complexity of the spectrum after 400 cm⁻¹ is probably due to the bending vibrations of isolated PO₄ tetrahedra, mixing with Al-0 vibrations in the $[Al_2O_6(OH)_3]$ chains, described by MOORE and ARAKI (1973) in the bjarebyite structure.

The numerous and strong frequencies from 900 cm^{-1} to 1200 cm^{-1} are these of the stretching vibrations of apparently distorded PO₄ tetrahedra.

The 871 cm^{-1} band is certainly the bending vibration of OH⁻ groups.

The region of the stretching vibrations of OH^- groups between 3200 and 3600 cm⁻¹ shows a large and strong band at 3250 cm⁻¹, proving the existence of OH^- groups with hydrogens bonds and a sharp doublet at 3520 and 3540 cm⁻¹ due to free OH^- groups. This deduction is in good agreement with observations of MOORE and ARAKI (1973). Indeed there are two $OH^$ sites, located in 0(8) and 0(9) in the bjarebyite structure. Following MOORE and ARAKI (1973), $0(9) = OH^-$ forms a hydrogen bond with 0(5), the distance being 2.60 Å and that appears in the IR spectrum at 3250 cm⁻¹. On the other hand the doublet is the stretching vibrations of OH⁻ groups located in 0(8) separated from 0(1) by a distance of 3.65 Å, too long to allow a hydrogen bond.

Conclusions

Bjarebyite, described in this paper, is to be added to the exceptionally long list of phosphate minerals occurring in Buranga mine. The new mineral is interesting and furnishes details about the geochemistry of this pegmatite.

From a geochemical point of view the presence of barium in the Buranga pegmatite is of some importance. In addition to the barium-rich bjarebyite, a barian arrojadite with 5.36 per cent BaO and another new barian phosphate containing 3.5 per cent BaO have been noted (VON KNORRING, 1972, 1973).

The paragenesis of bjarebyite in Buranga is also noteworthy. MOORE et al. (1973) described bjarebyite in Palermo from a complex association with the following phosphate minerals: amblygonite, augelite, childrenite, scorzalite and palermoite. This environment is nearly the same as that in Buranga. In this latter pegmatite it seems that Ca is more common than Sr, so the role of palermoite is taken by bertossaite.

Acknowledgments

The authors are indebted to Professor J. TOUSSAINT and M. VERMEIRE of the Institute of Crystallography, Univ. Liège for performing single crystal X-ray work.

We are very grateful to Professor P. TARTE of the Institute of Chemistry, Univ. Liège for recording IR spectra.

We wish to thank M. A. BERTOSSA for inviting one of us (O. v. K) to visit the Buranga pegmatite and collecting a large amount of samples. Visits to Leeds by one of us (A. M. F.) were supported by F.N.R.S. Grant, Belgium.

References

- ALTMANN, J. (1961): L'occurence de brazilianite, augelite, frondelite et lithiophilite dans la pegmatite de Buranga. Schweiz. mineral. petrogr. Mitt. 41, 407.
- Cox, A. A. (1967): A program for least squares refinement of unit cell dimensions. Cryst. Lab., Dept. Phys., Univ. London.
- GALLAGHER, M. J. and GERARDS, J. F. (1963): Berlinite from Rwanda. Miner. Mag. 33, 613.
- LARSEN, E. S. and BERMAN, H. (1934): The microscopic determination of the nonopaque minerals. Geol. Surv. U.S.A., Bull. 848.
- MOORE, P. B., LUND, D. H. and KEESTER, K. L. (1973): Bjarebyite (Ba, Sr) (Mn, Fe, Mg)₂ Al₂ (OH)₃ (PO₄)₃, a new species. Mineral. Rec. 4, 282–285.

- MOORE, P. B. and ARAKI, T. (1973): Bjarebyite Ba (Mn, Fe)²⁺ ₂Al₂ (OH₃) (PO₄)₃: its atomic arrangement. Amer. Mineral. 59, 567-572.
- THOREAU, J. and DELHAL, J. (1950): Les phosphates ferromanganésifères de la pegmatite de Buranga. IIIe congr. national des Sc., Bruxelles, p. 30–34.
- THOREAU, J. and BASTIEN, G. (1954): Les phosphates des pegmatites du Ruanda occidental. Bull. Acad. Roy. Sci. Colon. Bruxelles, XXV, p. 1595.
- THOREAU, J. and SAFIANNIKOFF, A. (1957): Triphylite, lithiophilite et phosphates associés du Congo belge et du Ruanda. Bull. Acad. Roy. Belg. serv. 5, 43, p. 324.
- von KNORRING, O. and HORNUNG, G. (1965): Pegmatite investigations in East Africa. 9th Ann. Rep. Res. Inst. African Geol. Univ. Leeds, 44.
- VON KNORRING, O. and MROSE, M. E. (1966): Bertossaite, a new mineral from Rwanda. Can. Miner. 8, 668.
- von KNORRING, O. (1969): A note on the phosphate mineralisation at the Buranga pegmatite, Rwanda. Bull. Serv. Geol. Rwanda, n° 5, 42–45.
- (1970): Mineralogical and geochemical aspects of pegmatites from orogenic belts of equatorial and southern Africa. In African Magmatism and Tectonics. (Eds T. N. Clifford and I. G. Gass) Oliver and Boyd, Edinburgh, 157–184.
- (1972): Note on phosphate minerals from Buranga pegmatite, Rwanda, 16th Ann. Rep. Res. Inst. Af. Geol. Univ. Leeds, 56–57.
- (1973): Notes on pegmatite minerals from Rwanda, Uganda and South West Africa.
 17th Ann. Rep. Res. Inst. Af. Geol. Univ. Leeds, 72–73.

Manuscript received 12. Oct. 1974.